

## TECHNICAL DATA SHEET

### Adhesive-General Specialty Board Coating 305505

#### PRODUCT DESCRIPTION:

**Adhesive 305505** is a formulated Hot Melt primarily designed for case and carton sealing. Adhesive 305505 will have excellent hot tack and excellent adhesion to wax and coated substrates. Adhesive 305505 will exhibit great high and low temperature bond performance.

#### TYPICAL PHYSICAL PROPERTIES:

**Viscosity<sup>1</sup>** 1,800cps (+/- 360) @ 350°F

**Softening Point** 225°F (+/- 2.0)

**Color** Amber

**Application Temperature** 330°- 360° F

<sup>1</sup> ASTM D 3236

**HANDLING & STORAGE:** For best results, use product within 365 days.

#### SAFETY:

When handling and working with hot melt adhesives wear protective clothing and eye protection at all times. To minimize the risk of flammable vapors, do not exceed 400°F melt temperature.

#### CLEAN UP:

For best results, allow product to cool and manually remove excess adhesive with scrapper. Consult your hot melt equipment manufacturer Pearson Packaging Systems representative for additional help.

#### FDA STATUS:

Consult your Pearson representative for the most recent FDA status information.

#### ROTATE STOCK:

For best results, used oldest lots first.

#### TOXICITY:

Under normal conditions of use this product is considered nontoxic. Consult the SDS for additional Information.



The information herein is general information designed to assist customers in determining whether our products are suitable for their applications. Our products are intended for sale to industrial and commercial customers. We require customers to inspect and test our products before use and to satisfy themselves as to contents and suitability for their specific applications. We warrant that our products will meet our written specifications. **Nothing herein shall constitute any other warranty express or implied, including any warranty of merchantability or fitness for a particular purpose**, nor is any protection from any law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is limited to replacement of our materials and in no event shall we be liable for special, incidental or consequential damages.

V17-001